



# QR-9000-GF30

## Nylon 4/6

2301 St. Joseph Industrial Park Drive Evansville, IN 47720 Phone 812/429-0901 Fax 812/429-0905 www.customcompounding.com

Appearance	<u>General Description</u> Natural/Black Color Custom Colors Available
Features	High Heat Resistance Heat Stabilized (PO Specified) Good Strength/Stiffness Oil Resistant, Chemical Resistant
Filler/Additive	30% Glass

<u>Property</u>	<u>Method</u>	<u>Value</u>	<u>Unit</u>
<i>-Physical</i>			
Specific Gravity	ASTM D792	1.5	
Melting Point		565	°F
<i>-Mechanical</i>			
Flex Modulus	ASTM D790	1,330,000	psi
Flex Strength @ Break	ASTM D790	31,300	psi
Notched Izod Impact, 73°F	ASTM D256	1.15	ft.lbs/in
Tensile Modulus	ASTM D638	1,530,000	psi
Tensile Strength @ Break	ASTM D638	21,600	psi
Tensile Elongation @ Break	ASTM D638	2.5	%
<i>-Thermal</i>			
Deflection Temp @ 264 psi	ASTM D648	535	°F
Deflection Temp @ 66 psi	ASTM D648	N/A	°F

These test results are based on reliable procedures. Due to variable conditions and methods of processing, no guarantees or warranties are expressed or implied including the implied warranty of merchantability and fitness for particular use. The above information is not to be construed as a license or a recommendation to infringe on any patents.

### *-Injection Molding*

#### Drying Conditions

Min 2 hours – Max 4 hours      185      °F

#### Cylinder

Rear      540-560      °F

Middle      560-590      °F

Front      570-590      °F

Nozzle      580      °F

#### Mold

Maximum      300      °F

Minimum      180      °F

Processing Temp      580-595      °F

Maximum Moisture Content      0.05      %

ISO9001:2000 Registered



The guidelines listed above are based on specimens at various thicknesses typical in manufacturing. These values are not intended to be used for specification purposes. These are recommended starting parameters. The equipment part design and tooling will influence final process parameters. The percent recycle is dependent on part design, wall thickness, process, and final performance requests.